

Aslon® OutdoorFIT

Material composition

Recycled granulate bound using a PU binding agent and possibly a colouring agent.

Dimensions and thicknesses

Dimensions: 500 x 500 mm | 1.000 x 1.000 mm


Thickness: 30 mm | 40 mm | 45 mm

Sizetolerance


±2%

±5%


Colours




Black



Red



Green



Grey

Density

800 kg/m³ | 900 kg/m³ | 1.000 kg/m³

Granulate

Standard 1-3 mm

Fire resistance

Efl to EN 13501

Smoke resistance

S2

Water permeable

920 mm/h


Noise reduction

ΔLw 25 DB EN 10140-1

Warranty

3 year warranty for wear resistance when used at gyms.


The warranty does not apply to colour.



WATER
PERMEABLE



SHOCK
ABSORBING



SOUND
ABSORBING

